

S-8016.B5

TYPE : Basic

AWS A5.5 / ASME SFA5.5 E8016-B5
EN 1599 - E CrMo5 B 1 2

Applications

S-8016.B5 can be used for welding of 0.5%Cr-1%Mo steel used for high temperature and high pressure boilers, chemical equipment and oil refining plants.

Characteristics on Usage

S-8016.B5 is a low hydrogen type electrode which is suitable for welding 0.5%Cr-1%Mo steel used at high temperature. The crack resistibility of all-weld is excellent.

Notes on Usage

- ① Preheat at 150~250°C(302~482°F) and postheat at 620~680°C(1148~1256°F).
- ② Dry the electrodes at 350~400°C(662~752°F) for 60 minutes before use.

Welding Position



1G 2F 3G 4G
(PA) (PB) (PF) (PE)

Current

AC or DC +

Typical Chemical Composition of All-Weld Metal (%)

C	Si	Mn	P	S	Cr	Mo
0.10	0.48	0.59	0.019	0.009	0.51	1.0

Typical Mechanical Properties of All-Weld Metal

YS MPa(lbs/in ²)	TS MPa(lbs/in ²)	EL (%)	Heat Treatment
555 (80,600)	663 (96,300)	27.8	690°C(1274°F) × 1hr. S.R

Approval

I Packing

Packet 5 kg (11 lbs)
Carton 5 kg (11 lbs) × 4 : 20kg(44 lbs)

Sizes Available and Recommended Currents (Amp.)

Size mm (in)	2.6 (3/32)	3.2 (1/8)	4.0 (5/32)	5.0 (3/16)	6.0 (15/64)
Length mm(in)	350 (14)	350 (14)	400 (16)	400 (16)	450 (18)
F	55~90	90~130	130~190	190~240	250~300
V-up, OH	50~80	80~120	120~170	-	-